

TECHNICAL DATA SHEET – CRS-2

DESCRIPTION

CRS-2 is a cationic rapid setting asphalt emulsion. Used primarily in the construction of chip seal. A rapid setting emulsion is one that will destabilize quickly when in contact with aggregate.

PHYSICAL PROPERTIES

- Boiling Point (°F): 212
- Specific Gravity (H₂O = 1): 1.01
- Solubility in Water: Dispersible
- Appearance and Odor: Brown liquid with Mild Petroleum Odor, Cures Black

PARAMETER	TEST METHOD	MIN	MAX
Tests on Emulsion			
Saybolt Furol Viscosity, SFS @ 50 °C	AASHTO T 72	100	400
Particle Charge	AASHTO T 59	Positive	
Sieve Test, %	AASHTO T 59	----	0.1
Residue by Distillation, %	AASHTO T 59	65	----
Oil Distillate, %	AASHTO T 59	----	0.5
Storage Stability, 24 hr, %	AASHTO T 59	----	1.0
Demulsibility, %	AASHTO T 59	40	----
Tests on Residue			
Penetration @ 25 °C, dmm	AASHTO T 49	40	100
Ductility @ 25 °C	AASHTO T 51	35	----
Solubility, %	AASHTO T 44	97.5	----

Storage		Application Temps	
Grade	Recommended Max Storage Temp	Recommended Range	Max Allowable
CRS-2	180°F	140-180°F	180°F

Transportation: USDOT Not Regulated

LIMITATIONS

Proper storage, handling, and application guidelines must be followed carefully for best results. As with any emulsion, do not allow the material to freeze or boil because of aggressive heating. CRS-2 IS NOT COMPATIBLE WITH ANIONIC EMULSIONS (RS, QS, SS, etc.). All equipment should be thoroughly cleaned if anionic emulsion was previously present.

CAUTION

For industrial use only. Refer to SDS for further information.

THIS PRODUCT IS NOT SUBJECT TO THE CONTROLLED PRODUCT REGULATIONS.

The information contained herein is the best information available to Quality Emulsions relating to our products, the use of our products, and is based on tests believed to be reliable. There is no warranty, EXPRESSED OR IMPLIED in association with this product or its use. Quality Emulsions assumes no liability for any damages incurred in association with the use of our products, and the liability of Quality Emulsions will be limited to the replacement of material found to be defective, or, at its option, the refund of the purchase price. Product information subject to change without notice.

Product information subject to change without notice.